

(12) UK Patent Application (19) GB (11) 2 124 635 A

- (21) Application No 8320646
 (22) Date of filing 1 Aug 1983
 (30) Priority data
 (31) 8222303
 (32) 2 Aug 1982
 (31) 8229726
 (32) 18 Oct 1982
 (33) United Kingdom (GB)
 (43) Application published
 22 Feb 1984
 (51) INT CL³
 C08L 41/00 23/26 25/04
 29/04 33/02 71/04 87/00
 (52) Domestic classification
 C3K 201 HA
 C3J AN
 C3M 102C 120 124 125
 133C 139C 146C A
 C3R 36C 36T2 7C 7N5A
 7N5B 7PX M PD
 C3W 203 211 215 217
 229 301 323
 U1S 1424 C3J C3K C3M

- (56) Documents cited
 None
 (58) Field of search
 C3K
 G2C
 (71) Applicant
 Raychem Limited,
 (United Kingdom),
 Rolls House,
 7 Rolls Buildings,
 Fetter Lane,
 London,
 EC4 1NL
 (72) Inventors
 Malcolm Gordon Cross,
 Robert Lines
 (74) Agent and/or address for
 service
 A. W. Jay, A. C. Dlugosz,
 J. E. Benson, R. L. Hall, D.
 C. Jones,
 Raychem Limited,
 Patent Department,
 Faraday Road,
 Dorcan,
 Swindon,
 Wiltshire

(54) Polymer composition

(57) Electrically conductive polymers, especially polypyrroles, are formed with a charged polymeric dopant supplying the necessary counter -ions to stabilise the charged conductive form of the conductive polymer. The physical properties of the conductive polymer can thus be usefully modified in ways different from those achieved by non-polymeric dopants or by

forming the conductive polymers in pre-existing bodies of non dopant (i.e. uncharged) polymers. Examples of the dopants which can be used are ionisable polysulphonate, poly(2-acrylamido-2-methylpropane sulphonic acid), sulphonated poly(2,5-dimethylphenyleneoxide), sulphonated polystyrene, sulphonated polyethylene, sulphonated styrene (hydrogenated) butadiene copolymer and ionisable polycarboxylate or polyphosphonate.

Best Available Copy

UD 2 124 635 A

SPECIFICATION

Polymer composition

This invention relates to compositions comprising an electrically conductive polymer.

5 Known electrically conductive polymers include polysulphur nitrides, polyanilines, polyacetylenes and polypyrroles. Although some polymers e.g. (SN)_x are intrinsically conductive, many polymers require oxidation (or reduction) to
10 render them significantly electrically conductive. For example, polyacetylenes require oxidation or reduction, polypyrroles require oxidation. The process of oxidation (or reduction) is often called doping and a counter-ion is required to associate
15 itself with the oxidised (or red⁺) polymer to balance the ionic charges therein. This counter-ion is often referred to as a dopant. Examples of dopant include BF₄⁻, p-toluene sulphonate, Br⁻.

In the interest of clarity, the phrase "electrically
20 conductive polymer" will be used herein to mean any polymer or oligomer inherently or intrinsically capable of electrical conductivity or semi-conductivity, (hereinafter both included in the terms "electrical conductivity" or "electrically
25 conductive"), regardless of whether or not oxidation/reduction of the polymer and/or the presence of a "dopant" is or are required or present actually to render it electrically
30 conductive. Thus, the aforesaid phrase includes inorganic polymers such as the polysulphur nitrides, and organic polymers such as the polypyrroles, and particularly includes the organic polymers whether in the "doped" electrically
35 more conductive state, or in the "undoped" or "dedoped" electrically less conductive state.

The terms "doping" and "de-doping" will be taken to mean the oxidation/reduction processes used to convert the polymers between their less
40 conductive and more conductive states; the term "dopants" will refer to the aforementioned counter-ions and to the materials used to provide the counter-ions which stabilise the more
45 conductive form of the polymers; and the terms "un-doped", "doped" and "de-doped" will be understood accordingly.

The present invention provides a polymer composition comprising an electrically conductive polymer associated with a polymeric dopant
50 which stabilises the polymer in an electrically conductive state.

It will be understood that the "polymeric dopant" specified in accordance with the present invention is a material in which the necessary counter-ions are provided by a polymer or
55 oligomer molecule having charged groups in the polymer backbone and/or as side chains or pendant groups, examples of such a polymeric dopant including polymers and oligomers carrying ionisable sulphonate, carboxylate, or phosphonate
60 groups, polyelectrolytes, and ionenes (generic name for ionic amines).

The use of a polymeric dopant according to the present invention leads to very considerable

65 example, the physical and/or chemical characteristics of the polymeric dopant can be used to modify those of the conductive polymer itself. Furthermore because the modifying
70 polymer is also the dopant, it can be drawn into the conductive polymer during formation of the latter in a solution of the dopant to form a modified polymer film which will have different properties from those which can be achieved by forming a conventionally doped conductive
75 polymer in a solvent-swollen pre-formed film of another polymer. Also, because the polymeric dopant will tend to interpenetrate with the conductive polymer, it can provide an intimate
80 combination of the materials which will be highly resistant to undesired loss of dopant and de-doping.

Thus, further aspects of the present invention provide (1) a method of making an electrically
85 conductive polymer, comprising bringing the polymer from an electrically less conductive state to an electrically more conductive state in the presence of a polymeric dopant which stabilises the polymer in the more conductive state; (2) a method of making an electrically conductive
90 polymer comprising polymerising an appropriate monomer in the presence of a polymeric
95 dopant capable of stabilising the electrically conductive polymer in an electrically conductive state; (3) a method of making an electrically conductive polymer comprising polymerising an appropriate monomer and bringing it into an electrically conductive state
100 in a solution of a polymeric dopant capable of stabilising the polymer in the electrically conductive state; and (4) a method of making an electrically conductive polymer comprising providing the conductive polymer in
105 association with a monomer which is polymerisable to produce *in situ* a polymeric dopant capable of stabilising the conductive polymer in an electrically conductive state, and preferably including the step of polymerising the said monomer to produce the dopant.

The specific choice of polymeric dopant will
110 depend on the nature of the conductive polymer to be formed. Positively charged dopants may be appropriate when negatively charged conductive polymers such as polyacetylenes are involved.
115 Examples of positively charged polymeric dopants are ionenes of formula (I), (II), or (III) in the accompanying formula drawings; acrylamide copolymers such as copoly(acrylamide) (3-acrylamido-3-methylbutyltrimethyl ammonium
120 chloride) of formula (IV) on the accompanying formula drawings; and polymers of 2-methylene ammonium or 2-methylenesulphonium salts of 1,3-butadiene, of formula (V) in the accompanying formula drawings. In the formula
125 drawings, R represents suitable organic substituent groups and n, x, y are integers of suitable value, suitable groups and integers being readily identifiable by persons familiar with this field of technology.

more likely to be of interest, especially in connection with polypyrroles, which are a preferred class of electrically conductive polymers in view of their resistance to degradation on aging. An outstanding advantage of the present invention is the possibility of producing flexible, self-supporting films of polypyrroles, which tend to be undesirably brittle and difficult to handle. Examples of negatively charged polymeric dopants are ionisable polysulphonates such as salts of poly(2-acrylamido-2-methyl-propane-sulphonic acid) or its copolymers with acrylamides or alkyl methacrylates, sulphonated polystyrene, sulphonated polyepichlorohydrin, sulphonated poly(2,5-dimethyl-phenylene oxide), sulphonated polyphenylether sulphones (or ketones), and sulphonated polyethylene, of formula (VI) to (XI) respectively in the accompanying formula drawings; polyvinylsulphonic acid sodium salt (m.w.=2000), polyacrylic acid (m.w.=90,000), polymaleic acid, sulphonated EPDM, being an elastomer, could also advantageously be used; polycarboxylates such as salts of polyacrylic acid and copolymers of acrylic acid; and phosphonated polymers such as that indicated by formula (XII) in the accompanying formula drawings. The negatively charged groups may be on the polymer backbone and/or on pendant side chains, and the polymers may be aromatic and or aliphatic in nature. Copolymers and/or mixtures and blends of the above dopants can be used.

It should be noted that the polymeric dopant itself may provide a certain amount of ionic conductivity, but this is usually clearly distinguishable from the intrinsic electronic conductivity of the conductive polymer.

As aforesaid, an especially interesting class of electrically conductive polymers comprises polypyrrole and its derivatives, which may be prepared from pyrrole or suitably substituted derivatives thereof, as generally indicated by formula (XIII) in the accompanying formula drawings, sufficient positions being left unsubstituted to permit the required polymerisation. Electrically conductive polymers are generally believed to operate by way of a conjugated pi-electron system, and it will be understood that some substituents or combinations of substituents may interfere with the conjugated system so as to detract from or destroy the desired electrical conductivity, acceptable substituents being readily determinable by simple testing the conductivity of the resulting polymer.

Other classes of electrically conductive polymer which may benefit from the use of polymeric dopants according to the present invention include polymers of anilines and naphthylamines of formula (XIV) and (XV); and conjugated polymers such as polyacetylenes and polyphenylenes.

The electrically conductive polymers with polymeric dopants according to the present invention may be prepared in several different ways.

Electrochemical methods of preparing

follows to produce the polymer-doped materials of the present invention. In general, an electrochemical cell is used, wherein two electrodes (made from, for example, stainless steel, platinum or Indium oxide coated glass) are immersed in an electrolyte mixture, suspension or solution. The electrolyte includes a polymer carrying groups which are ionisable into an appropriately charged ionic dopant species. The solvent or mixture of solvents may be chosen from protic and aprotic solvents, for example acetonitrile, tetrahydrofuran, dimethyl formamide, water, methanol. To the electrolyte mixture is added the monomer species that is to be oxidatively polymerised to form the desired electrically conductive polymer. Stirring of the resulting mixture may be required to achieve a homogeneous mixture. Upon operation of the cell, an electrically conducting film is formed on the appropriate electrode. With positively charged polymers such as polypyrroles, the film is formed on the anode and is partially oxidised and contains a negatively charged polymer dopant to provide charge neutrality to the film.

Chemical preparative methods can also be used, in which the monomer and the polymeric dopant are mixed with an oxidising agent in a suitable liquid vehicle. The oxidising agent can advantageously be carried by the polymeric dopant of the present invention, for example by forming the ferric salt of a dopant such as sulphonated polystyrene, thereby bringing about simultaneous oxidative polymerisation and doping with the negatively charged polymeric dopant.

This ingeniously avoids or reduces the degree of doping with inorganic anions, which would occur if ferric chloride were used as the oxidising agent.

Some specific examples of the present invention will now be described, in which electrical conductivity was measured by a 4-probe method similar to that described in "Organic Semiconducting Polymers", Ed. J.E. Katon, (Marcel Dekker 1968).

Sulphonated polymeric dopants were obtained as follows, unless otherwise stated in the Examples.

Sulphonated Polyethylene

Commercially available chlorosulphonated polyethylene (density 1.28) containing 1.1% by wt. S, which indicates a degree of sulphonation of approx. 2% by weight, was hydrolysed with NaOH to convert the SO_2Cl groups to $-\text{SO}_3^-\text{Na}^+$ (see Formula XI) and used in this form as the electrolyte in the electrochemical doping experiments.

Sulphonated polystyrene

Polystyrene (Average molecular not 70,000) was treated with chlorosulphonic acid and the product was subsequently hydrolysed to give an acidic ionisable polymer, that contained 3.23% by wt. S (degree of sulphonation approx. 12% by

Sulphonated poly(2,5-dimethylphenylene oxide)

Commercially available poly(2,5-dimethylphenylene-oxide) was treated with chlorosulphonic acid and subsequently hydrolysed to give an acidic ionisable polymer, containing 3.54% by wt. S (degree of sulphonation approx. 16% by wt.).

Preparation of sulphonated poly(vinyl alcohol)

- 10 24.8 g Chlorosulphonic acid added slowly with rapid stirring to 100 mls pyridine. This solution was added to a suspension of 8.8 g poly(vinyl alcohol) of molecular weight 14000 in 100 ml. pyridine. The mixture was heated at 90°C for one
- 15 hour with continuous stirring, allowed to cool to room temperature and solids were removed by vacuum filtration. The solids were re-dissolved in 200 mls distilled water; 100 mls of water were then removed on a rotary evacuator, and the
- 20 remaining solution was acidified with 50 mls 1M HCl. The polymer was precipitated by addition of methanol, redissolved in water and reprecipitated with methanol, washed with methanol and dried over P_2O_5 under vacuum.

- 25 Degree of sulphonation=25% by weight determined by sulphur content.

Preparation of a sulphonated styrene (hydrogenated) butadiene copolymer

- 30 800 mls dichloromethane were placed in a 2 litre round bottomed flask fitted with 500 ml dropping funnels, high speed stirrer, reflux condenser, N_2 inlet and gas outlet attached to inverted funnel/ H_2O gas absorber. One of the dropping funnels contained 20 g of a
- 35 commercially available styrene- (hydrogenated) butadiene copolymer dissolved in 500 mls dichloromethane the other funnel contained 3.6 mls chlorosulphonic acid in 500 mls dichloromethane.

- 40 The reaction flask was cooled at 5°C and kept at this temperature during the addition of the reactants. The solutions of chlorosulphonic acid and the polymer were added at the same slow rate over approximately 3 hours. Rapid stirring was maintained throughout the addition. After
- 45 addition was complete stirring was continued and the reaction maintained at 5°C for 16 hours. The temperature was allowed to rise to room temperature and the reaction left stirring for a
- 50 further 24 hours. The reaction was monitored by the quantity of HCl liberated. The HCl was measured by titrating the water in the gas absorber with 1M NaOH using phenolphthalein indicator.

- 55 The dichloromethane was removed from the precipitated polymer by a combination of decanting, filtration and rotary evacuation. The

polymer was dissolved in THF and precipitated by addition with rapid stirring to distilled water. THF was removed from the water/polymer suspension by rotary evaporation and the polymer filtered.

NaOH C^{13} NMR shows addition of sulphonic acid to be on aromatic section of polymer.

- 65 Sulphur content=4.8%. This can be altered by time of reaction.

Example 1

- Two stainless steel electrodes 2 cm apart were employed as the anode and cathode of an electrolytic cell, having an electrolyte mixture consisting of 1 g commercially available (Aldrich) poly(2-acrylamido-2-methyl propane sulphonic acid) in a mixture of 37 cc water and 10 cc acetonitrile, together with 0.06 moles of pyrrole. During
- 70 the operation of the cell the mixture was stirred.

- 75 The electrolytic cell was powered by a D.C. power supply. Electrolysis of the electrolyte mixture was carried out by applying to the cell an electrical potential of 5V for a period of one hour,
- 80 during which time the current density was 5 $mAcm^{-2}$.

- A black film (33 microns thick) was deposited on the anode and was removed to give a free-standing film that was tough and flexible while
- 85 wet. After drying in air the film was brittle, and could not be creased or folded in two like paper without fracturing. The "dry" film had a room temperature conductivity (4 probe measurement) of 25 Scm^{-1} .

Example 2

- A similar procedure to that of Example 1 was followed but this time employing as the electrolyte a solution of 2 g of the acid form of sulphonated poly(2,5-dimethylphenylene oxide) in
- 95 75 cc water. The cell was operated at a current density of 5 $mAcm^{-2}$ for 45 minutes. A black free standing film 36 microns thick was obtained that was extremely tough and flexible when wet. When dry the film was very brittle and had a room
- 100 temperature conductivity of 0.3 Scm^{-1} .

Example 3

- The procedure of Example 2 was repeated, but this time employing as the electrolyte a solution of 2 g of the acid form of sulphonated poly(2,5-dimethylphenylene oxide) in 50 cc DMF, and the polymerisable species used was aniline (0.02 moles), at a current density of (6 $mAcm^{-2}$ for 45
- 105 minutes.

- A black film was deposited on the anode and could be removed to give (it is believed for the first time) a free-standing film consisting substantially only of polyaniline and dopant. The film was very brittle, and the sample was too small for conductivity to be determined.
- 110

Example 4

- The procedure of Example 1 was followed, but this time employing as the electrolyte 5 g of the sodium salt of sulphonated polyethylene in a mixture of 1.5 cc of water and 50 cc of tetrahydrofuran, at a current density of 1 $mAcm^{-2}$ for a
- 120 period of one hour. A black film was deposited on the anode and

and stretchable (30% elongation to break) both when wet and when dry, with a dry conductivity of about 10^{-3} Scm^{-1} .

Example 5

5 The procedure of Example 1 was followed but this time employing as the electrolyte mixture, 2 g of the sodium salt of sulphonated polystyrene in 50 cc acetonitrile, at a current density of 1 mAcm^{-2} for 45 minutes.

10 A shiny black film was formed on the anode and when dry was very brittle. (Conductivity not determined).

Example 6

Sulphonated poly(vinyl alcohol)

15 0.03 moles of pyrrole were dissolved in 30 mls of a solution of 2 g 25% sulphonated poly(vinyl alcohol) in 50 mls DMF and 20 mls water. This solution was electrolysed for one and a half hours at a current density of 10 mAcm^{-2} on stainless steel electrodes as in Example 1. A black film of polypyrrole doped with sulphonated polyvinyl alcohol was removed from the anode. The film was 0.24 mm thick and had a conductivity of 2.56 Scm^{-1} . The dry film was tough but brittle.

Example 7

Poly(methacrylic acid)

25 0.045 moles of pyrrole were dissolved in 50 mls of a solution of 10 g poly(methacrylic acid) supplied by BDH in 40 mls water and 50 mls methanol. This solution was electrolysed for one and a half hours at a current density of 10 mAcm^{-2} on stainless steel electrodes. A black film of polypyrrole doped with poly(methacrylic acid) was removed from the anode. The film was 0.09 mm thick and had a conductivity of 1.70 Scm^{-1} .

The dry film was brittle.

Example 8

Sulphonated styrene (hydrogenated) butadiene copolymer

40 An electrolysis solution was prepared by dissolving pyrrole (5% v) in a solution of the sulphonated polymer (2% wt.) in tetrahydrofuran:nitrobenzene (75/25 v/v). This solution was electrolysed in a cell consisting of a solid stainless steel anode and a stainless steel gauze cathode separated by 5 mm. A constant current of 1 mAcm^{-2} was passed for 20 minutes. Stirring of the electrolyte was maintained through the electrolysis. The polypyrrole film was peeled from the anode and washed in tetrahydrofuran and then dried under vacuum at 50°C . Film thickness was 0.4 mm.

Physical properties

55 The film was smooth on one side (electrode side) and very rough on the other (solution side). The smooth side has a conductivity of $5 \times 10^{-3} \text{ Scm}^{-1}$ while the rough side was essentially non-conductive. Examination of the film under a

pressure to give a completely smooth film. Also, by folding the film in half and hot pressing a film conductive on both sides was obtained.

Film as prepared: thickness 0.4 mm, ultimate elongation 410%, stress at failure 18 MPa.

Pressed film: thickness 0.27 mm, ultimate elongation 390%, stress at failure 32 MPa.

Claims

1. A polymer composition comprising an electrically conductive polymer associated with a polymeric dopant which stabilizes the polymer in an electrically conductive state.
2. A composition according to claim 1, wherein the conductive polymer is positively charged and the dopant is negatively charged.
3. A composition according to claim 2, wherein the conductive polymer is a polymer of aniline or a substituted aniline.
4. A composition according to claim 2, wherein the conductive polymer is a polymer of pyrrole or a substituted pyrrole.
5. A composition according to claim 2, 3 or 4, wherein the polymeric dopant is an ionisable polysulphonate.
6. A composition according to claim 5, wherein the dopant is poly(2-acrylamido-2-methylpropane sulphonic acid), sulphonated poly(2,5-dimethylphenylene oxide), or sulphonated polystyrene.
7. A composition according to claim 5, wherein the dopant is sulphonated polyethylene.
8. A composition according to claim 5, wherein the dopant is sulphonated styrene (hydrogenated) butadiene copolymer.
9. A composition according to claim 2, 3 or 4, wherein the dopant is an ionisable polycarboxylate or polyphosphonate.
10. A composition according to claim 2 substantially as described in any one of the foregoing Example 1 to 8.
11. A self-supporting film comprising an electrically conductive polymer associated with a polymeric dopant which stabilises the polymer in an electrically conductive state.
12. A self-supporting film according to claim 11, comprising substantially only the conductive polymer and the dopant, wherein the conductive polymer is a polymer of aniline or a suitably substituted aniline.
13. A self-supporting film of a composition according to any of claims 2 and 4 to 10, wherein the conductive polymer is not a polymer of aniline or substituted aniline.
14. A self-supporting film according to any of claims 11 to 13 having a greater concentration of the conductive polymer at one of its surfaces and a greater concentration of the dopant at the other of its surfaces.
15. A method of preparing an electrically conductive polymer, comprising polymerising an appropriate monomer in the presence of a polymeric dopant capable of stabilising the electrically conductive polymer in an electrically

16. A method according to claim 15, wherein the monomer is polymerised in a solution of the polymeric dopant.

7. A method according to claim 15 or 16, wherein the polymerisation is carried out electrochemically.

18. A method according to claim 15 or 16, wherein the polymerisation is effected chemically.

19. A method according to any of claims 15 to 18, wherein the conductive polymer requires oxidation to bring it into an electrically conductive state, and such oxidation is carried out during and/or after the polymerisation.

20. A method according to claim 19, wherein the oxidation is effected by means of an oxidising agent bonded to the polymeric dopant.

21. A method of preparing an electrically conductive polymer comprising bringing the polymer from an electrically less conductive state to an electrically more conductive state in the presence of a polymeric dopant which stabilises the electrically conductive polymer in the electrically more conductive state.

22. A method of preparing an electrically conductive polymer comprising providing the conductive polymer in association with a monomer which is polymerisable to produce *in situ* a polymeric dopant capable of stabilising the conductive polymer in an electrically conductive state.

23. A method according to claim 22, including the step of polymerising the said monomer to produce the said dopant.

24. A method according to any of claims 15 to 23, wherein the conductive polymer is positively charged and the dopant is negatively charged.

25. A method according to claim 20, wherein the conductive polymer is a polymer of aniline or a substituted aniline.

26. A method according to claim 20, wherein the conductive polymer is a polymer of pyrrole or a substituted pyrrole.

27. A method according to claim 24, 25 or 26, wherein the dopant is a polysulphonate.

28. A method according to claim 27, wherein the conductive dopant is poly(2-acrylamido-2-methylpropanoic acid), sulphonated poly(2,5-dimethylphenylene oxide), or sulphonated polystyrene.

29. A method according to claim 27, wherein the dopant is a sulphonated polyethylene.

30. A method according to claim 27 wherein the dopant is a sulphonated styrene (hydrogenated) butadiene copolymer.

31. A method according to claim 24, 25 or 26 wherein the dopant is an ionisable polycarboxylate or polyphosphonate.

32. A method according to claim 15, substantially as described in any one of the foregoing Examples 1 to 8.

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

☒ **BLACK BORDERS**

☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**

☐ **FADED TEXT OR DRAWING**

☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**

☐ **SKEWED/SLANTED IMAGES**

☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**

☐ **GRAY SCALE DOCUMENTS**

☒ **LINES OR MARKS ON ORIGINAL DOCUMENT**

☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**

☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.